













GRES PORCELLANATO IMPASTO COLORATO

Colored Body Porcelain Stoneware / Grès Cérame Masse Coloré / Feinsteinzeug mit Eingefärbten Scherben

UNI EN 14411 B1a Allegato G (ISO 13006)

Caratteristica tecnica Technical feature Caractéristique technique Technische Eigenschaft	Norma Norm Norme Norm	Valore richiesto dalle norme Required standards Valeur prescrite par les normes Normvorgabe	IKON		
			Naturale	Outdoor	
 <p>Lunghezza e larghezza / Length and width Longuer et largeur / Länge und breite</p> <p>Spessore / Thickness / Epaisseur / Stärke</p> <p>Rettilineità spigoli / Straightness of sides Rectitude des aretes / Kantengeradheit</p> <p>Ortogonalità / Rectangularity Orthogonalite / Rechtwinkligkeit</p> <p>Planarità / Length and width Planeite de surface / Ebenflächigkeit</p>	UNI EN ISO 10545-2	N ≥ 15 cm		Conforme Corresponding Conforme Entsprechend	
		%	(mm)		
		± 0,6 Non Rect. ± 0,3 Rect	± 2,0 Non Rect. ± 1,0 Rect		
		± 5 ± 0,5 Non Rect. ± 0,3 Rect	± 0,5 ± 1,5 Non Rect. ± 0,8 Rect		
		± 0,5 Non Rect. ± 0,3 Rect	± 2,0 Non Rect. ± 1,5 Rect		
± 0,5 Non Rect. ± 0,4 Rect	± 2,0 Non Rect. ± 1,8 Rect				
 <p>Qualità della superficie Surface quality Qualités de la surface Oberflächenqualität</p>	UNI EN ISO 10545-2	Il 95 % min. delle piastrelle di prova deve essere esente da difetti visibili Minimum 95% of the tested tiles must be free from visible defects 95% min. des carreaux de test ne doit pas contenir de défauts visibles Min. 95% der geprüften Fliesen dürfen keine sichtbaren Mängel aufweisen		Conforme Corresponding Conforme Entsprechend	
 <p>Assorbimento d'acqua / Water absorption Absorption d'eau / Wasseraufnahme</p>	UNI EN ISO 10545-3	≤ 0,5% Individual max 0,6%		≤ 0,5%	
 <p>Sforzo di rottura / Breaking strength Effort de rupture / Bruchkraft</p>	UNI EN ISO 10545-4	S ≥ 1300 N (≥ 7,5 mm)		S ≥ 1300 N	
 <p>Resistenza alla flessione / Modulus of Rupture Résistance à la flexion / Biegefestigkeit</p>	UNI EN ISO 10545-4	R ≥ 35 N/mm²		R ≥ 35 N/mm²	
 <p>Resistenza all'abrasione (metodo PEI) Abrasion resistance (PEI test) Résistance à l'abrasion (méthode PEI) Widerstand gegen Abrieb (nach PEI)</p>	UNI EN ISO 10545-7	Segnala la classe di abrasione e i cicli superati Report abrasion class and cycles passed		WALNUT PEI 4 AMBER - BIRCH PEI 5	
 <p>Resistenza al gelo / Resistance to frost Résistance aux gel / Frostbeständigkeit</p>	UNI EN ISO 10545-12	Richiesto Required		Non gelivo / Frost-proof Non gèlifs / Frostsicher	
 <p>Resistenza ai prodotti chimici Resistance to chemical products Résistance aux produits chimiques Widerstand gegen Chemikalien</p>	UNI EN ISO 10545-13	Resistenza a basse concentrazioni di acidi e alcali Resistance to low concentrations of acids and alkalis Secondo la classificazione indicata dal fabbricante Manufacturer is to state classification		LA	LA
		Resistenza ad alte concentrazioni di acidi e alcali Resistance to high concentrations of acids and alkalis Metodo di prova disponibile Test method available		HA	HA
		Resistenza ai prodotti chimici di uso domestico ed agli additivi per piscina Resistance to household chemicals and swimming pool salt Classe minima B Minimum class B		A	A
 <p>Resistenza alle macchie Staining résistance Resistance aux taches Widerstand gegen Fleckenbildung</p>	UNI EN ISO 10545-14	Min. 3		Conforme Corresponding Conforme Entsprechend	
 <p>Resistenza agli sbalzi termici Thermal shock resistance Résistance aux écarts de température Temperaturwechselbeständigkeit</p>	UNI EN ISO 10545-9	Metodo di prova disponibile Test method available		Resiste Resistant Résiste Widerstandsfähig	
Caratteristiche accessorie / Additional features					
 <p>Stabilità dei colori / Colours stability Stabilité des couleurs / Farbbeständigkeit</p>	DIN 51094	Colorazione Stabile Stable coloring		Conforme / Corresponding Conforme / Entsprechend	
Caratteristiche di sicurezza / Safety characteristics					
 <p>Resistenza allo scivolamento Slip resistance Résistance au glissement Rutschemmende Eigenchaft</p>	METOD O B.C.R.A	μ > 0,40		Conforme / Corresponding Conforme / Entsprechend	
	DIN EN 16165	ANNEX A Test della rampa a piedi nudi / Classe dichiarata Barefoot ramp test / Declared Class Méthode de la rampe pieds nus / Classe déclarée Methode der schiefen Ebene, barfuß / Angegebene Klasse		-	A+B+C
		ANNEX B Test della rampa a piedi calzati / Classe dichiarata Shod ramp test / Declared Class Rampe avec chaussures / Classe déclarée Methode der schiefe Ebene, mit Schuhwerk / Angegebene Klasse		R10	R11
	DCOF (ANSI A 326.3)	≥ 0,42		Conforme / Corresponding Conforme / Entsprechend	